

TECHNICAL DATASHEET



ABS

SN0121SLG

Physical	Test Condition	Typical Value Unit	Test Method
Melt Index	220°C/10kg	9.5 g/10min	ISO 1133

Mechanical	Test Condition	Typical Value Unit	Test Method
Tensile Strength Yield	50mm/min	31 MPa	ISO 527
Charpy NotchImpact	23°C 1eA	10 kJ/m ²	ISO 179

Optical performance	Test Condition	Typical Value Unit	Test Method
Gloss	60°	15 %	ASTM D523

Thermal	Test Condition	Typical Value Unit	Test Method
Vicat 50°C/hr 50N		97.5 °C	ISO 306

Product Packaging

25kgs Bag

<https://sntpolymer.com/>