

# TECHNICAL DATASHEET

---



## EVA

SN0628ELH

Item	Test results Unit	Inspection Method
Melt mass flow rate	5.5 g/10min	Q/LHX F810-2016
VA contents	27.5 wt%	Q/LHX F813-2016
Density	0.951 g/cm <sup>3</sup>	GB/T 1033.1
Tensile breaking stress	12 MPa	GB/T 1040.2
Elongation at Break	1200 %	GB/T 1040.2
Melting temperature	74 °C	ASTM D3418
Vicat softening temperature	43 °C	ASTM D1525

## Product Packaging

---

25kgs Bag

---