

TECHNICAL DATASHEET



E-glass Direct Roving

SN2000GHJ

Item	Test value	Unit	Standard value	Test Method
Linear density Tex	2021	%	2000±5	GB/T18369-2008
Tensile Breaking Strength N/Tex	0.45	—	≥0.30	GB/T18369-2008
Loss of Ignition	0.29	%	0.50±0.30	GB/T18369-2008
R2O Content	0.75	%	≤0.80	GB/T18369-2008
Moisture Content	0.02	%	≤0.10	GB/T18369-2008
Appearance	Up to Grade	—	—	GB/T18369-2008

Product Packaging

25kgs Bag
